

Description

Crest Inhibiseal is a clear brown liquid formulated to impart an inhibitive seal on phosphated surfaces. It promotes increased salt spray resistance in an iron phosphate system or a cleaning system. The pH of the solution and the concentration of the product are the two most important tests to achieve increased salt spray results.

- » Contains no heavy metals such as chromium.
- » Non-flammable solution.
- » Used in very low concentrations.
- » Stops flash rusting in the dryer.
- » Increases salt spray resistance of painted parts.

Method of Use

Application Methods

- » Immersion

Mixing Instructions

1. Use at a concentration of 0.5 to 1 pint of product to every 100 gallons of water in the tank
2. Ensure pH is between 4.5 and 5.5.
3. The temperature of the product should be 70° to 120°F (The higher temperatures make the parts dry faster).
4. Paint should be applied within 4 hours to get maximum corrosion protection.
5. This tank is dumped every 60 to 180 days.

Product should be stored at no lower than 50°F and no higher than 100°F.

Caution

Refer to product labels and Safety Data Sheets for precautionary and handling information.

Warranty and Liability Disclaimer

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience; however, since conditions of actual use are beyond our control, any recommendations, or suggestions, are made without warranty, expressed or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.