

Description

Crest PPC-34 is a liquid compound specifically formulated to process iron, galvanized steel, aluminum, and steel at low to medium temperature where a cleaner/iron phosphate coating is required. It may be used in either a three stage or a five stage washer system to provide improved paint adhesion and corrosion protection.

Specifications

This product meets or exceeds all qualifications for the following:

- » Federal Specification TT-C-490F Type II Class A and B

Method of Use

Application Methods

- » Immersion
- » Flood

Mixing Instructions

- » Add 6-8 gallons of PPC 34 of every 100 gallons of water.

Adjustments

- » This system should be cleaned every 3 to 6 months.
- » Check with your Crest representative on when and how this should be done.

General Operating Parameters

Concentration	6 to 8% by volume
Temperature (°F)	110° to 160°F
Time	45 to 120 seconds
pH	3.6-5.0

Equipment

- » For tanks and heaters, mild steel is recommended.

Caution

Refer to product labels and Safety Data Sheets for precautionary and handling information.

Product should be stored at no lower than 50°F and no higher than 100°F.

Warranty and Liability Disclaimer

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience; however, since conditions of actual use are beyond our control, any recommendations, or suggestions, are made without warranty, expressed or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.