

Glare's DTM - 03500

Description

Glare's DTM 03500 is specially developed by using modified fast drying alkyd

Product data

Product code

03500

Gloss

Smooth and Matt

Volume solids (%)

50 ± 5

Specific gravity (kg/L)

1.25 ± 0.02

Application

Mixing ratio	NA
Thinner	Glare's Thinner 03400
Pot life (Hour)	NA

Film Thickness

Dry film (Micron)	35-40
Wet film (Micron)	70-80
Theoretical spreading rate (m ² /L)	12-14 (By Brush)

Drying and overcoating

Touch dry (Min.)	5-10.
Hard dry (Hour)	1-1.5.
Overcoating (Hour)	After 2 hrs.

Storage

Shelf life (Months)	12
---------------------	----

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

GLARECOAT PRIVATE LIMITED

www.glarecoat.com