

## Glare's DTM - 06500

### Description

Glare's DTM 06500 is a special product based on Nitrocellulose and alkyd resin

### Product data

#### Product code

06500

#### Gloss

Matt

#### Volume solids (%)

45±5

#### Specific gravity (kg/L)

1.25 ± 0.1

### Application

Mixing ratio	NA
Thinner	Glare's Thinner 06400
Pot life (Hour)	NA

### Film Thickness

Dry film (Micron)	35- 40
Wet film (Micron)	70-80
Theoretical spreading rate (m <sup>2</sup> /L)	10-12 (By Brush)

### Drying and overcoating

Touch dry (Min.)	15-25
Hard dry (Hour)	3-4.
Overcoating (Hour)	3-4.

### Storage

Shelf life (Months)	18
---------------------	----

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

**GLARECOAT PRIVATE LIMITED**

[www.glarecoat.com](http://www.glarecoat.com)