

Glare's Intermediate - 02200

Description

Glare's Intermediate 02200 is quick drying primer based on modified synthetic alkyd Resin with an excellent adhesion and durable film is widely used in refinishing field as well as original equipment manufacturers as it has quick drying properties with very good adhesion and corrosion resistance on metal substrate.

Product data

Product code

02200

Gloss

Matt

Volume solids (%)

50±5

Specific gravity (kg/L)

1.2 ± 0.1

Application

Mixing ratio	NA
Thinner	Glare's Thinner 02400
Pot life (Hour)	NA

Film Thickness

Dry film (Micron)	30
Wet film (Micron)	50-60
Theoretical spreading rate (m ² /L)	12- 14 (By Brush)

Drying and overcoating

Touch dry (Min.)	10-15.
Hard dry (Hour)	1-2.
Overcoating (Hour)	1-2.

Storage

Shelf life (Months)	12
---------------------	----

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

GLARECOAT PRIVATE LIMITED

www.glarecoat.com