

Glare's Top coat- 02300

Description

Glare's Top coat 02300 is Quick drying is based on Synthetic modified alkyd. It gives tough, flexible high gloss finish with excellent leveling. The dried film withstand abrasion, scratch and impact resistances. It can be applied by dip application also. Protective coating for structural steel, pipe, Scaffolding, Drum, vehicles, industrial and agricultural machineries.

Product data

Product code

02300

Gloss

Glossy

Volume solids (%)

55 ± 5

Specific gravity (kg/L)

1.05 ± 0.1

Application

| | |
|-----------------|--------------------------|
| Mixing ratio | NA |
| Thinner | Glare's Thinner 02400 |
| Pot life (Hour) | NA |

Film Thickness

| | |
|--|------------------|
| Dry film (Micron) | 30-40 |
| Wet film (Micron) | 70-80 |
| Theoretical spreading rate (m ² /L) | 10-12 (By Brush) |

Drying and overcoating

| | |
|--------------------|--------|
| Touch dry (Min.) | 10-15. |
| Hard dry (Hour) | 2-3. |
| Overcoating (Hour) | 2-3. |

Storage

| | |
|---------------------|----|
| Shelf life (Months) | 12 |
|---------------------|----|

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

GLARECOAT PRIVATE LIMITED

www.glarecoat.com