

Glare's Top coat- 05300

Description

Glare's Top Coat 05300 PU paint is 2k System designed to cross link at room temperature. Base part is acrylic copolymer which reacted with polyisocyanates.

Product data

Product code

05300

Gloss

Matt, SG or Glossy as per requirement

Volume solids (%)

45 ± 5

Specific gravity (kg/L)

1.05 ± 0.1

Application

Mixing ratio	0.167361111
Thinner	Glare's Thinner 05400
Pot life (Hour)	4-6 hrs.

Film Thickness

Dry film (Micron)	40-50
Wet film (Micron)	90-100
Theoretical spreading rate (m ² /L)	12-14 (By Brush)

Drying and overcoating

Touch dry (Min.)	15-20.
Hard dry (Hour)	4-6.
Overcoating (Hour)	4 -6.

Storage

Shelf life (Months)	10
---------------------	----

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

GLARECOAT PRIVATE LIMITED

www.glarecoat.com