

Glare's Top coat- 07300

Description

HR paint is specially developed product for various application where heat resistance to specific temperature range is required.Hr 250 paint is designed for temperature resistance up to 250 °C.

Product data

Product code

07300

Gloss

Glossy/ Matt/ Semiglossy

Volume solids (%)

40-42

Specific gravity (kg/L)

1.25 ± 0.2

Application

| | |
|-----------------|--------------------------|
| Mixing ratio | NA |
| Thinner | Glare's Thinner 07400 |
| Pot life (Hour) | NA |

Film Thickness

| | |
|--|--------------------|
| Dry film (Micron) | 40-45 |
| Wet film (Micron) | 90-100 |
| Theoretical spreading rate (m ² /L) | 10-12.5 (By Brush) |

Drying and overcoating

| | |
|--------------------|--------------|
| Touch dry (Min.) | 30-45 |
| Hard dry (Hour) | 1.5-2. |
| Overcoating (Hour) | After 2 hrs. |

Storage

| | |
|---------------------|----|
| Shelf life (Months) | 12 |
|---------------------|----|

Shelf life from date of production, when stored in original, unopened containers.

Handling : Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Glare's Safety Data Sheet for this product along with the Product Data Sheet.

For professional use only.

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. For updated detail ;please contact Glarecoat Private Limited.

GLARECOAT PRIVATE LIMITED

www.glarecoat.com