
Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Gravity
Product Name	Gravity
Product Description	Aluminium Skirting Board Profile
Item No	GRV
Area of Use	Public, Office, Residantial
Material	EN AW 6463 T6, EN AW 6061 T6
Length	2500mm
Surface	Anodised

Gravity aluminum skirting board is a specially designed profile that is attached to the lower edges of the wall and provide a neat and clean appearance to carpeted areas. Gravity aluminum skirting board profile not only provides a seamless transition between the floor and the wall, but also provides protection for carpet edges. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing. Gravity provides a perfect transition with the floor. Plasterboard or ceramic wall coverings are applied on the profile, creating a flush appearance with the wall. Gravity aluminum skirting board profile can be easily installed by applying tile adhesive to the joints extensions. Corners can be assembled by cutting profile to 45 degree. Gravity aluminum skirting board has a matte anodized coating option in silver color.





Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

Damage caused by impact

Damage caused by scratching

Damage caused by abrasive substance or chemical cleaning agents contact

Damage caused by prolonged contact with water Damage caused by exposure to intense temperature Damage caused by montage













ALLOY DATASHEET EN AW 6463 T6 [AlMq0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress Rp0,2 min Mpa	Tensile Strength Rm min Mpa	Elongation Min A50mm % - Max A %	Brinell Hardness
T4	e≤50	75	125	14 - 12	46
T5 T6	e≤50 e≤50	150 195	110 160	8 - 6 10 - 8	60 74

^{*} Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

Physical properties (approximate values, 20°C)

Density (kg/m³) 2700	Melting range (°C) 585-650	Electrical conductivity (MS/m) 28-34	Thermal conductivity (W/m.K) 200-220	Co-efficient of thermal expansion 10-6/K 23.4	Modulus of elasticity (GPa) ~70
----------------------------	----------------------------------	---	---	---	--

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AIMg5Cr(A) or AISi5, and AIMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be redured by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable

^{**} Hardness values are for indication only,

^{***} For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.