

1- CHARACTERISTICS

Resin **Norester 680 TPA** is a vinylester resin with excellent corrosion resistance it is thixotroped, promoted with cobalt and amine .

Excellent solvent and acid resistance. High flexural strength. High heat resistance.

Norester 680 TPA can be used for hand lay-up and spray-up, filament winding.

The Norester 680 TPA cures at ambient temperature with addition of MEKP.

2- PROPERTIES OF LIQUID RESIN

| | |
|---|--|
| <u>Brookfield viscosity</u> (ISO2555 - 20°C - sp3) | 5 rpm 1750 mPa.s 50 rpm 800 mPa.s |
| <u>Specific gravity</u> (ISO 1675 – ICON 012) | 1.10g/cm ³ |
| <u>Geltime</u> (ICON 002) (20°C – 2% MEKP on 100gr) | 15 – 20 minutes |

| | |
|--|--------------|
| <u>Acid value</u> | 12 mgKOH / g |
| <u>No volatile content</u> (ICON 003) | 62% |

3- PROPRIETES DE LA RESINE POLYMERISEE

| | |
|---------------------------------------|-----------|
| <u>Shrinkage</u> volume | 8.3% |
| <u>Flexural strength</u> (ISO 178) | 149.6 MPa |
| <u>Flexural modulus</u> (ISO 178) | 8.3 GPa |
| <u>Tensile strength</u> (ISO 527) | 120 MPa |

| | |
|---|--------|
| <u>Elongation at break</u> (ISO 527) | 3 - 4% |
| Temperature of deflection under load (ISO 75-3) | 145 °C |
| <u>Barcol hardness</u> (ASTM 2583) | 50 |

4- APPLICATION ADVICES

To obtain optimum characteristics, it is necessary to add a peroxyde MEKP. Be careful not to add less than 1% of MEKP or more than 3% of MEKP.

5- PACKAGING

Available in cans of 25 kg and in drums of 225 kg.

6- STORAGE CONDITIONS AND HANDLING

Minimum storage life : 3 months.

The resin is subject to the Highly Flammable Liquids Regulations 1972. The resins should be stored under cool conditions in closed, opaque containers at a temperature not exceeding 25°C. Avoid exposure to heat sources such as direct sunlight.

Nous garantissons la conformité de nos produits avec les spécifications données ci-dessus. Nous dégageons toute responsabilité pour tout dommage ou perte causée suite à une mauvaise utilisation du produit.