White BOPP Film

OPP OpaqueFilm





High cavitation, heat-sealable on both sides, coronatreated on one side

Description

White film and high cavitation with a combination that produces excellent stiffness, opacity and whiteness. This film contains a package of migratory/non-migratory slip and anti-static additives to provide excellent machinability over a wide range of process conditions. The untreated side offers a wide sealing range. The corona treatment is on the outside side of the reel.

Main Characteristics

- Highly cavitated.
- Excellent opacity and whiteness.
- Crown side for excellent adhesion of inks and adhesives.
- Wide sealing range.
- Excellent flatness and dimensional stability.

Applications

Designed to be used in laminated structures as well as in monolayers. It is primarily used in applications that require high stiffness versus good performance such as wrap-around labels for beverages, canned products, among others. Due to its high opacity, this film is used in minimal transparency packaging applications. It complies with FDA and EU regulations for food contact.

* Important Considerations

* It is recommended to store this material at conditions not exceeding 30°C, under shade and with a relative humidity of 60%. To protect against humidity and avoid film blocking, rolls should stay covered with the plastic overwrap when not in use.

* The information in this data sheet is based on tests carried out in our laboratories and it is intended to be used for reference only, and does not constitute a specification; therefore, should not be construed as a guarantee of performance. It is the responsibility of the user to carry out the necessary tests to guarantee its use for the intended applications.

* This product complies with FDA and EU regulations. For more detailed information about our technical and regulatory documents, please visit our website: https://www.obengroup.com/en/documents

www.obengroup.com

Rev. Mar-2024

Standard
Dimensions

		Thickness	Yield		Core	22 ½" Φ Outside Diam.		30" Φ Outside Diam.		
s *	Film Code	(mils)	(in²/lb)	Width (in)	Size	Length (ft)	Weight (Ib/in)	Length (ft)	Weight (lb/in)	Treatment
	OC 30	1.18	39,100			23,000		46,000		
	OC 35	1.38	33,500	15 to 80	3" & 6"	19,700	7.05	39,400	14.05	Outside
ot size	OC 40	1.57	29,400			17,400		34,500		

*This product has lot s and width restrictions. Please consult your sales representative.

Typical Values							
of Physical							
Properties **							

**Information and data presented in this data sheet is intended to be used as general guidelines.Physical properties specifications are available upon request.

Dronorty	Unit	Testing Method	Thickness in Mils			
Property		Testing Method	1.18	1.38	1.57	
Light Transmission		%	ASTM D1003	30	25	20
Gloss 45°	Т	70	ASTM D2457	60		
Coefficient of Friction - Kinetic	N/N	-	ASTM D1894	0.35		
Tanaila Otwanath	DM	lb/in ²		11,700		
Tensile Strength	DT	ID/III-		21,800		
Elongation at Break	DM	%	ASTM D882	150		
Elongation at break	DT	70	ASTIVI DOOZ	40		
Secant Modulus 2%	DM	lb/in ²		101,600		
Secant Modulus 2 %	DT	ID/III*		145,100		
Surface Tension		dyn/cm	ASTM D2578	38		
Heat Seal Initiation Temperature		°F	ASTM F2029		221	
Seal Strength (284°F, 40 psi, 1s)	N/N	g/in	ASTM F88		400	

