

BOPP Film

OPP TapeFilm





Plain, one side corona treated

Description

Film that delivers high transparency, excellent gloss and rigidity due to its homopolymer layer. It is formulated with a PP copolymer to provide excellent good lamination bonds. The corona treated side is located on the outside face of the reel.

Main Characteristics

- Excellent mechanical properties.
- High gloss and transparency.
- Good thermal resistance.
- Outstanding flatness and dimensional stability.
- Corona treated outside suitable for excellent bonds to inks and adhesives.

Applications

This product is designed to be used as base film for adhesive tape applications as it presents excellent bond strengths to a variety of adhesives. Additionally, this film can be employed in other converting and food packaging industries where heat seals are not required. It meets the FDA regulations for direct food contact.

* Important Considerations

- It is recommended to store this material at conditions not exceeding 30°C, under shade and with a relative humidity of 60%. To protect against humidity and avoid film blocking, rolls should stay covered with the plastic overwrap when not in use.
- -The information in this data sheet is based on tests carried out in our laboratories and it is intended to be used for reference only, and does not constitute a specification; therefore, should not be construed as a guarantee of performance. It is the responsibility of the user to carry out the necessary tests to guarantee its use for the intended applications.
- This product complies with FDA and EU regulations. For more detailed information about our technical and regulatory documents, please visit our website: https://www.obengroup.com/en/documents

Standard Dimensions *

*This product has lot size and width restrictions. Please consult your sales representative.

Film Code	Thickness (mils)	Yield (in²/lb)	Width (in)	Core Size	22 ½" Φ Outside Diam.		30" Φ Outside Diam.		
					Length (ft)	Weight (lb/in)	Length (ft)	Weight (lb/in)	Treatment
TH 20	0.79	38,900	400 to 2,000	3" & 6"	37,100	11.43	68,600	21.1	Corona outside
TH 25	0.98	31,100			29,900		54,800		
TH 30	1.18	26,000			25,000		45,700		

Typical Values of Physical Properties **

**Information and data presented in this data sheet is intended to be used as general guidelines.Physical properties specifications are available upon request.

Droporty	Unit	Testing Method	Thickness in Mils				
Property		resung Method	0.79	0.98	1.18		
Haze Gloss 45°		%	ASTM D1003	2.0			
			ASTM D2457	90			
Coefficient of Friction - Kinetic		-	ASTM D1894	0.3			
Tanaila Strangth	DM	lb/in²		23,300			
Tensile Strength	DT	ID/III-		43,600			
Flangation at Proofs	DM	% ASTM D882		150			
Elongation at Break	DT	90	ASTIVI DOOZ	50			
Consist Madulus 00/	DM	lb/in²		188,600			
Secant Modulus 2%	DT	ID/III²		290,100			
Surface Tension	Т	dyn/cm	ASTM D2578	38			
Water Vapor Transmission Rate (100.4 °F, 90 % R.H.)		g/(100 in ² .day)	ASTM F1249	0.42	0.36	0.3	
Oxygen Transmission Rate (73.4 °F, 0 % R.H.)		cm3/(100 in ² .day)	ASTM D3985	142	116	103	

